

3M

Scotch-Grip™

Plastic Adhesive

1099 • 1099-L

Technical Data

October, 2002

Features

- 3M™ Scotch-Grip™ Plastic Adhesive 1099 is a medium viscosity grade for most brush or flow applications.
- 3M™ Scotch-Grip™ Plastic Adhesive 1099-L is a low viscosity grade for spray application.
- Fast drying.
- Provides strong, flexible bonds.
- Resists weathering, water, fuels, oil and plasticizers.
- Bonds vinyl extrusions and sheeting. (May stain light colored vinyls).
- Also bonds fabrics, foams and many plastics. (Not recommended for polyolefin plastic bonding).
- May be heat cured to obtain superior physical properties.

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Product	Scotch-Grip 1099	Scotch-Grip 1099-L
Viscosity (approx.): Brookfield RVF @ 80°F (27°C)	2000-4000 cps. (#3 sp @ 10 rpm)	200-325 cps. (#2 sp @ 20 rpm)
Solids Content (by wt.):	31 - 37%	22 - 26%
Base:	Nitrile Rubber	Nitrile Rubber
Color (wet & dry):	light tan	tan
Net weight (approx.): (lbs./gallon)	7.3 - 7.5 lbs./gal.	7.0 - 7.4 lbs./gal.
Flashpoint (closed up):	0°F (-18°C)	0°F (-18°C)
Solvent:	Acetone	Acetone and Methyl Ethyl Ketone (MEK)
Bonding Range: (10 mil wet film 2 surfaces)	Up to 40 minutes	Up to 20 minutes
Coverage: (@ 2.5 gms./ft.² dry wt.)	456 sq. ft./gal.	313 sq. ft./gal.

Scotch-Grip™ Plastic Adhesive 1099 • 1099-L

Handling/Application Information

Directions For Use:

- 1. Surface Preparation:** Remove all dust, dirt, oil, grease, wax, loose paint, etc. Wiping with 3M™ Scotch-Grip™ Solvent No. 3*, methyl ethyl ketone (MEK)* or 3M™ Citrus Base Industrial Cleaner* will aid in preparing the surface for bonding.
- 2. Application Temperature:** For best results the temperature of the adhesives and surfaces should be at least 65°F (18°C).

- 3. Application:** Stir well before using.

Porous Surface(s): Brush, flow or spray a thin, even coat of adhesive to one or both surfaces. Coating both surfaces is preferred since it gives greater strength and permits longer open time before bonding. Very absorbent materials may require more than one coat. Bond while adhesive is still wet or aggressively tacky. Join surfaces with firm pressure.

Non-Porous Surface(s): Brush, flow or spray a thin, even coat of adhesive to both surfaces. Allow adhesive to dry until tacky. Join surfaces with firm pressure.

- 4. Drying Time:** Drying time depends on temperature humidity, air movement, and porosity of the materials bonded. Greater immediate strength may be obtained by heat or solvent reactivation. See Reactivation below.
- 5. Reactivation:** To solvent reactivate, coat both surfaces with adhesive. Allow to dry tack-free. Lightly wipe one surface with a solvent such as Scotch-Grip Solvent No. 3* or methyl ethyl ketone (MEK)*. Complete bond within 30 seconds.

To heat reactivate, coat both surfaces with adhesive. Allow adhesive to dry completely. Reactivate by heating one or both surfaces to a minimum of 180°F (82°C). Assemble immediately (while hot), using firm pressure to ensure contact.

- 6. Curing:** 3M™ Scotch-Grip™ Plastic Adhesive 1099, 1099-L may be heat cured to obtain superior properties. Cure assembled parts at time and temperature listed using 100 psi pressure on the bond line.

Temperature of Bondline	Time for Minimum Cure
200°F (93°C)	120 minutes
240°F (116°C)	40 minutes
280°F (138°C)	12 minutes
320°F (160°C)	8 minutes
360°F (182°C)	5 minutes
400°F (204°C)	2 minutes

- 7. Cleanup:** Excess adhesive may be removed with Scotch-Grip Solvent No. 3* or methyl ethyl ketone* or acetone* preferably while adhesive is still wet.

***Note:** When using solvents, extinguish all ignition sources, read and follow the manufacturer's precautions and directions for use when handling such materials.

Scotch-Grip™ Plastic Adhesive 1099 • 1099-L

Application Equipment Suggestions

Appropriate application equipment can enhance adhesive performance. We suggest the following application equipment for the user's evaluation in light of the user's particular purpose and method of application.

1. Pumping:

3M™ Scotch-Grip™ Plastic Adhesive 1099, 1099-L*

5 Gallon or less dispensing system:

Pressure pot 100 psi operating pressure. Fluid hose should be nylon lined.

55 Gallon dispensing system:

Pump – 2:1 ratio, double acting, ball type checks, bung mounting, divorced design.

*Synthetic materials such as packings, seals and hose lines must be resistant to the solvent in these adhesives. Nylon, Compar, and Teflon® lined or coated parts are suggested.

2. Spray:

Scotch-Grip 1099-L:

Production Type Spray Equipment

Spray Gun	Air Cap	Fluid Tip	Air Pressure	Approximate Air Requirement ¹	Fluid Flow ²
DeVilbiss JGA, MSA	777	FX	65 psi	16 CFM	5 fl. oz./min.
Binks No. 95 or 2001	63PB	63BSS	65 psi	16½ CFM	6 fl. oz./min.

Note: This adhesive is not recommended for airless spraying.

¹2-3 H.P. Compressor for intermittent use.

4 H.P. Compressor for continuous use.

²To Measure Fluid Flow: Pressurize fluid source only; pull trigger; flow material into measuring device for 60 seconds, increase or decrease fluid source pressure to obtain desired fluid flow.

All material hoses should be nylon or PVA lined.

3. Brush/Roller: Typical brushes designed for oil based paints may be used.

Typical Adhesive Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Scotch-Grip 1099 and 1099L

180° Peel Strength Canvas/Steel			Overlap Shear Strength* Alum./Alum.	
Time @ 75°F (24°C)	Test Temp.	Value (lbs./in. width)	Test Temp.	Value (psi)
1 day	75°F (24°C)	16.5	-67°F (-55°C)	2989
3 days	75°F (24°C)	26	-30°F (-34°C)	3409
5 days	75°F (24°C)	23.5	75°F (24°C)	1306
7 days	75°F (24°C)	27.5	150°F (65°C)	897
2 weeks	75°F (24°C)	31	180°F (82°C)	643
3 weeks	75°F (24°C)	30	200°F (93°C)	607
After 3 weeks	-30°F (-34°C)	17.5	250°F (121°C)	467
After 3 weeks	150°F (66°C)	7		
After 3 weeks	180°F (82°C)	3.5		

*Bonds heat cured @ 300°F (177°C) for 30 minutes with 100 psi pressure on the bondline.

Scotch-Grip™ Plastic Adhesive

1099 • 1099-L

Storage Store product at 60-80°F (16-27°C) for maximum storage life. Higher temperatures reduce normal storage life. Lower temperatures cause increased viscosity of a temporary nature. Rotate stock on a “first in-first out” basis.

Shelf Life When stored in the original unopened container, under the conditions recommended, 3M™ Scotch-Grip™ Plastic Adhesive 1099, 1099-L have a shelf life of 15 months.

Precautionary Information Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

For Additional Information To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/adhesives. Address correspondence to: 3M Engineered Adhesives Division, 3M Center, Building 220-7E-01, St. Paul, MN 55144-1000. Our fax number is 651-733-9175. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

Important Notice 3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's method of application. Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Limitation of Remedies and Liability If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.

ISO 9002

This Engineered Adhesives Division product was manufactured under a 3M quality system registered to ISO 9002 standards.

3M

Engineered Adhesives Division
3M Center, Building 220-7E-01
St. Paul, MN 55144-1000



Recycled Paper
40% pre-consumer
10% post-consumer

Teflon is a registered trademark of E.I. DuPont de Nemours, Co.

3M and Scotch-Grip are trademarks of 3M.

Printed in U.S.A.

©3M 2002 78-6900-1426-7 (10/02)